

## Bostik FP404 Fire Retardent PU Foam FIRE RETARDENT POLYURETHAN PU FOAM



### Product Description

Bostik FP404 Fire Retardent PU Foam is a 1- component fire resistant polyurethane foam which offers a fire resistance of up to 120 minutes. In combination with other Bostik FireProtect® products Bostik FP404 Fire Retardent PU Foam reaches up to 240 minutes of fire resistance! Professional polyurethane fills and fixes foam with a structure of fine cells. High thermal and acoustic insulation.

### Benefits

- Tested according to EN 1366-4
- For use in joints from 5 mm to 30 mm wide
- Combined with Bostik FP 402 Fireseal Silicone in joints from 5 mm to 40 mm wide
- Separately applied, fire resistant up to 2 hours, combined with other Bostik FireProtect® products up to 4 hours
- Fire behaviour B1
- Fast processing
- Tack free after 8 to 12 minutes

### Applications

Bostik FP404 Fire Retardent PU Foam was specifically developed for fire resistant sealing and filling of joints and seams in certain areas where fire resistance is required. Fire resistance tested according to EN 1366-4 up to 60 minutes in a 20 mm wide gap. In combination with Bostik FP402 Fireseal Silicone, Bostik FP404 Fire

Retardent PU Foam will provide up to 180 minutes fire resistance in a 40 mm wide gap. In combination with Bostik FP403 Fireseal Hybrid, Bostik FP404 Fire Retardent PU Foam will provide up to 240 minutes fire resistance in a 40 mm wide gap. Ensure that you choose the correct fire resistance for your application by consulting the classification and test reports.

### Directions Of Use

Canister temperature: +5°C to +30°C (Recommended +15°C till +25°C). Application temperature (Environment and substrates): +5°C to +35°C. (Recommended +15°C till +25°C). When applying in cold conditions allow the canister to reach room temperature before use. Remove cap and screw the straw firmly onto the valve. Shake the canister vigorously prior to use at least 30 times. To apply foam, turn the canister upside down and press the adaptor. Half fill the cavity and, in case of low humidity, lightly spray the foam with water. The foam will expand to fill the rest. When fixing window frames, use spacers and wedges to hold the frame in place for approximately 24 hours until the foam is fully cured. Protect eyes and wear gloves and working clothes. Floor-covering and furniture to be covered with paper or plastic foil. Joints wider and deeper than 4 cm should be filled in multiple layers. Waiting time between applications 15-30 minutes. Before each application lightly spray with water. Only use in well ventilated areas. Store canister upright between +5°C and +25°C. Pressurized container! Protect from sunlight and do not expose to temperatures exceeding 50°C. Do not pierce or burn, even after use. Contains flammable propellants. Do not spray on a naked flame or any incandescent material. Keep away from sources of ignition. No smoking.

### Bostik Benelux B.V

Denariusstraat 11, 4903 RC Oosterhout, The Netherlands  
Phone: +31 (0)162491000, E-mail: [info@bostik.com](mailto:info@bostik.com)  
[www.bostik.com](http://www.bostik.com) | [www.denbraven.com](http://www.denbraven.com)

20-01-2023  
16:40:21  
CET

## Bostik FP404 Fire Retardent PU Foam

### FIRE RETARDENT POLYURETHAN PU FOAM

#### Additional information

Application temperature		+10°C to +35°C
Base		Polyurethane
Closed cells		± 70%
Curing time		100 – 120 minutes
Cutting time	EN 17333-3	60 – 80 minutes
Density		20-30 kg/m <sup>3</sup>
Fire behaviour	DIN 4102-1	B1
Tack free time	EN 17333-3	10 – 15 minutes
Temperature resistance		-40°C to +90°C
Thermal conductivity		30-35 mW/m.K
Total foam yield	EN 17333-1	750 ml = 25-30 liter

*These are typical values*

#### Limitations

- Not suitable for continuous water immersion or use in enclosed spaces
- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates

#### Surface Preparations and Finishing

Substrates must be clean and free of dust, oil and grease. It is important to moisten substrates slightly before use as this improves adhesion and finished cell structure of the foam.

#### Paintability

Paintable with water based and synthetic paints. We recommend testing compatibility with paint prior to application.

#### Cleaning

Fresh foam can be removed immediately with Bostik P100 Foam'N'Clean Power. After curing surplus foam can be removed with a knife or spatula and the foam surface can be finished.

#### Bostik Benelux B.V

Denariusstraat 11, 4903 RC Oosterhout, The Netherlands  
 Phone: +31 (0)162491000, E-mail: info@bostik.com  
 www.bostik.com | www.denbraven.com

#### Colour(s)

- Pink

#### Packaging

- Aerosol (handfoam)

*For product specifications, please refer to the Product Detail Page*

#### Shelf Life

If kept stored in a cool, dry place, in unopened original packaging, between +5°C and +25°C, shelf life is up to 18 months from production date. Store the canisters in an upright position.

#### Certifications

EMICODE EC1 Plus – very low emission
EN 1366-4:2006+A1:2010
EN 13501-2 Classification of fire resistance
DIN 4102-1 Reaction to fire
EN 13501-2:2007+A1:2009
TM1013_2017 Movement capability
VOC emissions ISO 16000

#### Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

#### Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification.

#### Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.

20-01-2023  
 16:40:21  
 CET